

VAUTID 200


Wear plate for highly wear resistant hardfacing
for medium to high impact



Distributed by



VAUTID Material characteristics



Base materials	All weldable steels, mostly structural steels
Material type Alloy components	High-chromium/high-carbon alloy on iron base with embedded special V and Ti carbides C – Cr – V – Ti – Fe
Recommended applications	For high abrasion, medium corrosion and medium to high impact. Maximum temperature 350° C
Weld deposit properties	Hardness (acc.DIN 32525-4): approx. 850 HV10, approx. 65 HRC*
Main industries	Metallurgical plants, cement industry, power stations, mining, sand and gravel industry, etc.
Typical machine parts	Transfer stations, chutes, grids, mill linings, etc.
Handling	<ul style="list-style-type: none"> - Conventional machining possible only by grinding - Thermal cutting using laser, plasma or water jet cutting - Cold working from diameter 300 mm possible with hard facing inside ⁽¹⁾ - Cold working from diameter 450 mm possible with hard facing outside ⁽¹⁾ - Fixing by welding or bolting on the base material - Constructions comparable with conventional steel construction

(1) dependent on thickness of plates

* subject to common industrial fluctuations

Forms of delivery:

Formats (mm)	Thickness of the plates Base material + Hardfacing (mm)	Material Layers	Comments
Standard formats 2.400 x 1.150 ⁽²⁾ 2.900 x 1.400 ⁽²⁾	5+3 ⁽³⁾ , 6+4, 6+6, 8+5, 8+6, 8+8, 10+5, 10+10 Further combinations on demand	≤ 6 mm: 1 Layer > 6 mm: 2 - 4 Layers	Base material 5 mm: Hardfacing 3 mm Base material 6 mm: Hardfacing 3 - 6 mm Base material ≥ 8 mm: Hardfacing 3 - 20 mm
Special body Up to 3.900 x 1.900 ⁽²⁾	On demand	≤ 6 mm: 1 Layer > 6 mm: 2 - 4 Layers	Base material 6 mm: Hardfacing 4 - 6 mm Base material ≥ 8 mm: Hardfacing 4 - 20 mm

(2) Hardfaced area
(3) max. 2.900 x 1.400 mm

This data sheet corresponds to the present state of production (October 2016) and can be changed anytime.